

◆ INTRODUCTION

Aluminum 5554 was developed as a filler alloy, primarily for alloy 5454 that is widely used in the manufacture of chemical storage tanks, automotive wheels, and in particular, those applications that may be subjected to temperatures in excess of 150 °F. This combination of alloys does not become sensitive to stress corrosion cracking at elevated temperatures.

◆ APPLICATIONS

- Welding filler wire

◆ GENERAL INFORMATION

- Non-Heat treatable
- ISO Designation: AIMg3Mn(A)
- Principle alloying elements: Magnesium, Manganese, Chromium, Titanium

◆ CHEMICAL COMPOSITION

<u>Silicon</u>	<u>Iron</u>	<u>Copper</u>	<u>Beryllium</u>	<u>Manganese</u>	<u>Magnesium</u>	<u>Zinc</u>	<u>Titanium</u>	Others	
								<u>Each</u>	<u>Total</u>
0.25	0.40	0.10	0.0008	0.50-1.0	2.4-3.0	0.25	0.05-0.20	0.05	0.15
<u>Aluminum</u>		<u>Chromium</u>							
Remainder		0.05-0.20							

Note: All values are maximum percentage, unless shown in range.



◆ PHYSICAL PROPERTIES

Melting Range:	1155-1195°F
Density, at 68°F:	0.097 lb/in ³
Resistance to Corrosion:	A (Gen) A (SCC)
Anodize Color:	White

◆ SPECIFICATIONS MEET or EXCEED

- ANSI/AWS A5.10 (ER & R 5554)

◆ STANDARD SIZES AND DIAMETERS

<u>Diameters</u>	<u>Package Form</u>
.030, .035, 3/64, 1/16, 3/32, 1/8	4 & 12 in. Spools
1/16, 3/32, 1/8, 5/32, 3/16, 1/4	Straight lengths

◆ TYPICAL MECHANICAL PROPERTIES OF GMAW GROOVE JOINT WELDS

<u>BASE ALLOY</u>	<u>BASE ALLOY</u>			<u>AS WELDED</u>		
	<u>UTS (KSI)</u>	<u>UYS (KSI)</u>	<u>ELONG (%)</u>	<u>UTS (KSI)</u>	<u>UYS (KSI)</u>	<u>ELONG (%)</u>
5454-0	36	17	22	35	16	17

◆ TYPICAL ULTIMATE TENSILE STRENGTHS AT, SELECTED TEMPERATURES OF GMAW GROOVE JOINT WELDS

<u>BASE</u>	<u>FILLER</u>	<u>-100°F</u>	<u>100°F</u>	<u>300°F</u>	<u>500°F</u>
5454	5554	32.0 KSI	31.0 KSI	26.0 KSI	15.0 KSI



Aufhauser
Corporation
39 West Mall
Plainview, NY 11803
Telephone:
516-694-8696
800-645-9486
Fax:
516-694-8690

Aluminum 5554

◆ TYPICAL GMAW PARAMETERS

Wire diameter	Range		Base material thickness	Suggested		Wire feed	Gas flow	Consumption 100 ft of weld
	Inches	Amps		Volts	Inches			
0.030	60-170	13-24	0.062	90	21	350	25	1.5
			0.094	100	22	560		1.8
			0.125	120	22	670		2
			0.187	140	23	780		4
0.035	70-180	15-26	0.062	100	21	350	35	1.5
			0.125	130	22	420		2
			0.250	170	23	640		6
0.047	140-260	20-29	0.094	100	22	150	45	1.8
			0.125	150	23	220		2
			0.250	190	24	320		6
			0.375	220	25	400		16
0.062	190-350	25-30	0.250	200	23	200	55	6
			0.375	230	24	220		16
			0.500	260	26	270		30
			0.750	280	27	300		50
			1.000	300	28	320		105
0.094	80-400	26-31	>1.000	350	30	180	60	150+

NOTE: Parameters based on flat position, groove joint, backing strip, and 100% argon gas.